

ECO-FLEX™ RTPV

Technical Data Sheet

SA-65A

Property	Test Method	Unit	Typical Properties
Specific Gravity	ISO 1183, Method A		1.03
Hardness	ISO 868, 15 sec delay	Shore A	65
Tensile Strength	ISO 37, Type 1, 50mm/min	MPa (psi)	3.8 (550)
Elongation at Break	ISO 37, Type 1, 50mm/min	%	415
100% Modulus	ISO 37, Type 1, 50mm/min	MPa (psi)	2.1 (310)
Tear Strength	ISO 34-1, Method B, Procedure b, 50mm/min	kN/m (pli)	21 (118)
Low Temperature Brittleness @ -40°C	ISO 812, Procedure A	Pass/Fail	Pass
Ozone Resistance	ISO 1431-1, Procedure A, 51 MPa, 20% Elongation	No Cracking	Pass
Flammability Resistance	SAE J369	mm/min	40
Heat Aging Resistance	ISO 188, 1008 Hours at 100°C in an air circulating oven followed by indicated property testing at 23°C		
Hardness Change		%	+2
Tensile Strength Change		%	+9
Elongation Change		%	+9

IMPORTANT: The following supersedes Buyer's documents. **SYNESIS MAKES NO REPRESENTATION OR WARRANTY, EXPRESS OR IMPLIED, INCLUDING OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE.** No statements herein are to be construed as inducements to infringe any relevant patent. Under no circumstances shall SYNESIS be liable for incidental, consequential or indirect damages for alleged negligence, breach of warranty, strict liability, tort or contract arising in connection with the product(s). Buyer's sole remedy and SYNESIS's sole liability for any claims shall be Buyer's purchase price. Data and results are based on controlled or lab work and must be confirmed by Buyer by testing for its intended conditions of use. The product(s) has not been tested for, and is therefore not recommended for, uses for which prolonged contact with mucous membranes, abraded skin or blood is intended; or fur uses for which implantation within the human body is intended.

SYNESIS

14555 Eby Rd. • Creston, OH 44217, USA • Phone: 330-769-4826 • Fax: 330-769-3850 • Email: info@ecoflexrtpv.com